

FORM PTO-1390 (Modified)
(REV 10-95)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

0327-0840-3 PCT

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

09/555371

INTERNATIONAL APPLICATION NO.
PCT/JP98/05167INTERNATIONAL FILING DATE
17 November 1998PRIORITY DATE CLAIMED
28 November 1997TITLE OF INVENTION
KITCHEN SHEETAPPLICANT(S) FOR DO/EO/US
Nobuya SATO, et al.

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
 - a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☒ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. ☒ A copy of the International Search Report (PCT/ISA/210).
8. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
9. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
10. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
11. ☐ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
12. ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).

Items 13 to 18 below concern document(s) or information included:

13. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☐ A **FIRST** preliminary amendment.
A **SECOND** or **SUBSEQUENT** preliminary amendment.
16. ☐ A substitute specification.
17. ☐ A change of power of attorney and/or address letter.
18. ☐ Certificate of Mailing by Express Mail
19. ☒ Other items or information:

Request for Consideration of Documents Cited in International Search Report

Notice of Priority

PCT/IB/304

PCT/IB/308

Page 2 of 2

DESCRIPTION

KITCHEN SHEET

Technical Field:

5 The present invention relates to a kitchen sheet having a diversity of uses. More particularly, it relates to a kitchen sheet having a diversity of uses, for example, in cooking or defrosting food in a microwave oven, wrapping food such as vegetables for preservation in a refrigerator, wrapping meat, fish, etc. for preservation in a freezer, steaming food in a steamer, etc., draining off food, absorbing impurities or fat exuded from food in boiling,
10 filtering oil, absorbing fat and oil, washing dishes, wiping a sink and a stove with a light scouring effect, and protecting dishes, etc. from breakage while stored, and as a draining sheet to remove water from garbage before discarding, as a filter of a ventilation fan, and so forth; and a process for producing the same.

Background Art:

15 In microwaving cooked food for re-heating or microwaving preserved cooked food, such as frozen food, for cooking, where the food is placed directly in a container, e.g., a plate, there has been the problem that the water vapor from the food is condensed into water on the plate, with which the food is swollen and, as a result, the texture is adversely affected.

To avoid this, a paper towel and the like can be put between the container and the food so
20 that the paper towel may absorb condensation to prevent the food from getting swollen.

As for steaming food, Japanese Patent Application Laid-Open No. 154573/92 proposes a food wrapping article having a prescribed water pressure resistance and a prescribed air permeability, describing that steamed an-man, etc. can conveniently be re-heated in the wrapping article. However, the number of the pieces of food or the size of
25 food that can be heated is limited by the kind of the food so that the article, while convenient for some specified foods, can hardly cope with unspecified forms of foods.

When a vegetable is kept in a refrigerator, it is wrapped in a plastic film or put into a plastic bag. However, since these materials have poor breathability, water vapor condenses

on the surface of the film or bag, and the water droplets gather into water to putrefy the vegetable.

Any of the state-of-the-art sheet articles, while excellent in performing a single function, is not susceptible of wide applications.

5 Disclosure of the Invention:

Accordingly, an object of the present invention is to provide a kitchen sheet having a diversity of uses in cooking or defrosting food in a microwave oven, wrapping food such as vegetables for preservation in a refrigerator, wrapping meat, fish, etc. for preservation in a freezer, steaming food in a steamer, etc., draining off food, absorbing impurities or fat
10 exuded from food in boiling, filtering oil, absorbing fat and oil, washing dishes, wiping a sink and a stove with a light scouring effect, and protecting dishes, etc. from breakage while storage, and as a draining sheet to remove water from garbage before discarding, as a filter of a ventilation fan, and so forth.

As a result of extensive studies, the present inventors have found that the above
15 object is accomplished by a sheet which comprises a base sheet comprising a fiber aggregate having a specific air permeability, the base sheet having been made uneven to have a specific apparent thickness, and which has a specific compressive recovery.

The present invention has been completed based on the above finding and provides a kitchen sheet characterized by comprising a base sheet comprising a fiber aggregate having
20 an air permeability of 5 cc/cm²/sec or more as measured in accordance with JIS L1096A, the base sheet having been shaped to have unevenness having an apparent thickness of 1.0 mm or greater, and having a compressive recovery of 30% or more.

The present invention also provides a process for producing a kitchen sheet characterized by comprising superposing nonwoven fabric of a thermoplastic resin on at
25 least one side of a sheet of a nonwoven fabric comprising an ultrafine hydrophobic fiber to obtain a base sheet having a water pressure resistance of 100 mmH₂O or more and less than 500 mmH₂O as measured in accordance with JIS L1092 and an air permeability of 5 cc/cm²/sec or more as measured in accordance with JIS L1096A and embossing the base sheet to impart unevenness so that the base sheet may have an apparent thickness of 1.0 mm

or greater and a compressive recovery of 30% or more.

The present invention also provides a process for producing a kitchen sheet characterized by comprising superposing nonwoven fabric comprising a thermoplastic resin on at least one side of a sheet comprising a nonwoven fabric comprising an ultrafine hydrophobic fiber to obtain a base sheet having a water pressure resistance of 500 mmH₂O or more as measured in accordance with JIS L1092 and an air permeability of 5 cc/cm²/sec or more as measured in accordance with JIS L1096A and embossing the base sheet to impart unevenness so that the base sheet may have an apparent thickness of 1.0 mm or greater and a compressive recovery of 30% or more.

10 Best Mode for Carrying out the Invention:

The kitchen sheet of the present invention will be described below in detail.

The kitchen sheet of the present invention comprises a base sheet comprising a fiber aggregate having an air permeability measured according to JIS L1096A (hereinafter simply referred to as an air permeability) of 5 cc/cm²/sec or more. The base sheet has been shaped to have unevenness so as to have an apparent thickness of 1.0 mm or greater, and the kitchen sheet has a compressive recovery of 30% or more.

The terminology "compressive recovery" denotes a compressive recovery R ($R(\%) = (Wc'/Wc) \times 100$) which is obtained from the work done in compressing Wc (gfc/cm²) and the work done in recovering from compression Wc' (gfc/cm²) when a sheet is compressed by applying a load of 50 gf/cm² at a stroke speed of 50 sec/min by use of KES-TB3 supplied by Katotec, Inc.

The base sheet which constitutes the kitchen sheet of the present invention and comprises a fiber aggregate has an air permeability of 5 cc/cm²/sec or more. When the kitchen sheet is used, e.g., in cooking or wrapping food, water vapor generated from the food can be dissipated because the base sheet has an air permeability of 5 cc/cm²/sec or more. If the air permeability of the base sheet is less than 5 cc/cm²/sec, condensation tends to collect on the kitchen sheet.

The higher the air permeability of the base sheet, the more suitable is the kitchen sheet as a filter of a ventilation fan or for use in steaming food in a steamer, re-heating in a microwave oven, and the like. However, with applicability to various uses being taken into

consideration, the air permeability is preferably 5 to 400 cc/cm²/sec, still preferably 30 to 200 cc/cm²/sec.

When the kitchen sheet is used to wrap food for pre-cooking in a microwave oven or to wrap a vegetable for preserving, too high an air permeability may let too much water evaporate from the food. Therefore, for use in pre-cooking in a microwave oven or for wrapping vegetables to be preserved, it is preferred for the base sheet to have an air permeability of 5 to 50 cc/cm²/sec.

The base sheet comprises a fiber aggregate having the above-described air permeability, the fiber material of the fiber aggregate being preferably hydrophobic fiber (particularly lipophilic fiber).

For the fiber material to be hydrophobic fiber is advantageous in that the resulting kitchen sheet, not absorbing water, is not wetted with water vapor, etc. coming from food while cooked, especially while re-heated in a microwave oven, so that the bottom of the food may be kept dry. There is another advantage that the preparation of the fiber aggregate is simple because the fiber aggregate as prepared needs no surface treatment, etc.

To use hydrophobic fiber is also favorable for adsorption of impurities, fat, etc. oozed from food while boiled.

Examples of the hydrophobic fibers are polyolefin resins, such as polyethylene and polypropylene, polyester resins, such as polyethylene terephthalate and polybutylene terephthalate, and copolymers thereof. Preferred among them are polyolefin resins, particularly polypropylene, from the standpoint of heat resistance and enhanced surface tension in microwaving, enhanced water pressure resistance, enhanced air permeability, and high lipophilic properties.

Hydrophilic fibers, such as rayon and cotton, and fibrous materials for papermaking, such as pulp, are also employable as the fiber material. Where the fiber aggregate is a laminate as hereinafter described, water- and oil-absorbing fiber can be used as an inner layer constituting the laminate to trap fat and water oozing from food.

These fiber materials can be used either singly or as a mixture of two or more thereof.

The above-described fiber materials preferably have an average fiber diameter of 0.1 to 100 μ m, particularly 1 to 50 μ m, especially 1 to 30 μ m.

Nonwoven fabric is preferably used as the fiber aggregate. Nonwoven fabric made up of fibers having an average fiber diameter of 0.1 to 100 μm (preferably 1 to 50 μm) is particularly preferred. Use of such nonwoven fabric makes it easy to control the air permeability of the base sheet and the compressive recovery of the resulting kitchen sheet within the prescribed ranges.

Adoptable methods for preparing the nonwoven fabric include spun bonding, spun lacing, melt blowing and flash spinning. While the air-through method, thermal bonding using a heat roll, needle punching, and the like are also employable, these methods need such a manipulation as the choice of the textile oil from among those useful as food additives.

The nonwoven fabric to be used preferably includes one comprising an ultrafine hydrophobic fiber (hereinafter referred to as an ultrafine hydrophobic fiber nonwoven fabric).

The hydrophobic fibers making up the ultrafine hydrophobic fiber nonwoven fabric preferably have an average fiber diameter of from 0.1 to 10 μm , particularly 0.1 to 5 μm .

Use of the ultrafine hydrophobic fiber nonwoven fabric makes it easy to control the air permeability of the base sheet within a prescribed range and to control the water pressure resistance of the base sheet within a preferred range. Further, because the fiber material of the nonwoven fabric has an increased total surface area, the kitchen sheet has an increased oil absorption and is therefore specially useful in applications requiring a certain degree of oil absorption, e.g., fat and oil absorption, skimming off fat and impurities, and heating deep-fried food in a microwave oven.

The ultrafine hydrophobic fiber nonwoven fabric can be prepared by melt blowing, flash spinning, or a like method.

The above-mentioned fiber aggregate can have a single layer structure comprising fiber of a kind or two or more different kinds or a laminate structure having two or more layers which may be the same or different. For example, the fiber aggregate may have a single layer structure, such as a single sheet comprising the above-described fiber nonwoven fabric or ultrafine hydrophobic fiber nonwoven fabric (i.e., a uniform sheet obtained by a

given process) or a laminate structure having two or more layers of nonwoven fabrics obtained by different processes.

In using a laminate having two or more layers as a fiber aggregate, it is preferred that the fiber material of the surface layer constituting the laminate be hydrophobic. The term "surface layer" as used herein is intended to mean the layer which constitutes the outer face of the kitchen sheet of the present invention.

The laminate can be produced by, for example, joining the layers into a unitary body by partial heat fusion.

Where the resulting kitchen sheet is intended to be used in contact with food, it is preferred that the side of the fiber aggregate to be brought into contact with food be composed of a layer of nonwoven fabric made of hydrophobic fiber. Where liquid absorbing properties are required as in fat and oil absorption, nonwoven fabric made of hydrophobic fiber may be combined with paper or nonwoven fabric made of water- and oil-absorbing fiber such as rayon.

Paper laminated with hydrophobic fiber nonwoven fabric on both sides thereof is convenient and preferred because the resulting laminate has no right side nor wrong side.

In order for the kitchen sheet of the present invention to be applicable to multiple purposes, it is preferred to use, as a base sheet, a laminate comprising a sheet of the above-described ultrafine hydrophobic fiber nonwoven fabric having provided on at least one side thereof nonwoven fabric comprising a thermoplastic resin (hereinafter referred to as thermoplastic resin nonwoven fabric). According to the use, a laminate of a combination of (A) hydrophobic fiber nonwoven fabric, (B) water- and oil-absorbing nonwoven fabric, e.g., of rayon, pulp or cotton, and (C) ultrafine hydrophobic fiber nonwoven fabric, such as A/B/C or A/B/C/B/A, is also useful.

The fiber material which can be used in the thermoplastic resin nonwoven fabric depends, as described below, on whether (1) the resulting kitchen sheet is designed to have no right nor wrong side or (2) the resulting kitchen sheet is designed to have the right and the wrong sides. For the kitchen sheet to have no right nor wrong side means that both sides of the sheet are either hydrophobic or hydrophilic.

In the case (1) wherein the resulting kitchen sheet is designed to have no right nor wrong side, the thermoplastic resin nonwoven fabric to be used is preferably one made of hydrophobic fiber as a fiber material (hereinafter referred to as hydrophobic nonwoven fabric). The hydrophobic fibers which can be used here include polyolefin resins, such as polyethylene and polypropylene, polyester resins, such as polyethylene terephthalate and polybutylene terephthalate, and copolymers thereof. In this case, the hydrophobic nonwoven fabric is provided on both sides of the ultrafine hydrophobic fiber nonwoven fabric.

On the other hand, in the case (2) wherein the resulting kitchen sheet has the right and the wrong sides, one of the sides could be of hydrophobic fiber with the other being of hydrophilic fiber. Accordingly, there is given a wider choice of fiber materials to be used in the thermoplastic resin nonwoven fabric than in the case (1). Examples of the fiber materials useful in the thermoplastic resin nonwoven fabric include hydrophilic fibers, such as rayon and cotton; and hydrophobic fibers, such as polyamide, e.g., nylon, polyolefin resins, e.g., polyethylene and polypropylene, polyester resins, e.g., polyethylene terephthalate and polybutylene terephthalate, and copolymers thereof.

The fiber material of the thermoplastic resin nonwoven fabric preferably has an average fiber diameter of from 8 to 100 μm , particularly 12 to 100 μm , especially 50 to 100 μm , taking into consideration dishwashing performance or wiping performance with a light scouring effect expected. With the fiber diameter being smaller than 8 μm , it is difficult to obtain dishwashing performance or wiping performance with a light scouring effect expected. On the other hand, if the diameter exceeds 100 μm , a large quantity of a material which contributes to a certain fiber density would be required, leading to an increase of cost.

Adoptable methods for preparing the thermoplastic resin nonwoven fabric include spun bonding and spun lacing. While the air-through method, thermal bonding using a heat roll, needle punching, and the like are also employable, these methods needs such a manipulation as the choice of the textile oil from among those useful as food additives.

It is not particularly essential for the ultrafine hydrophobic fiber nonwoven fabric used in the laminate to possess shapability to have unevenness and shape retention because it

is supported on the thermoplastic resin nonwoven fabric so that the laminate as a whole may secure shapability to have unevenness and shape retention as required. What is required of the ultrafine hydrophobic fiber nonwoven fabric is to have controllability so as to provide the base sheet with the water pressure resistance and the air permeability ranging in the respective prescribed ranges.

In order for the kitchen sheet of the present invention to be applicable to multiple purposes, the base sheet can be a laminate comprising a sheet of hydrophobic nonwoven fabric having provided on both sides thereof the above-described ultrafine hydrophobic fiber nonwoven fabric.

Use of this laminate brings improvements on shapability to unevenness by embossing and shape retention of the resulting kitchen sheet and also makes it possible to control dishwashing effects or cleaning performance with a light scouring effect expected. Therefore, further effects are expected.

The description of the hydrophobic nonwoven fabric used as the aforementioned thermoplastic resin nonwoven fabric applies to the hydrophobic nonwoven fabric used in this laminate as to examples of the fiber material, the average fiber diameter, the process of production, and the like.

The above-mentioned various laminates which are used in the kitchen sheet of the present invention contemplated for multiple purposes can be obtained by any laminating method with no particular restriction. For example, (a) fiber materials for nonwoven fabrics forming layers are prepared beforehand, and they are directly joined on top of each other into a unitary body by melt blowing, or (b) nonwoven fabric webs forming individual layers are separately formed and joined on top of each other into one body, or spun-bond nonwoven fabric and melt-blown nonwoven fabric are prepared simultaneously and joined together into one body. Joining nonwoven fabric webs in the method (b) can be carried out by heat fusion (the nonwoven fabric webs forming the respective layers are thermally joined into one body) or with an adhesive, which is selected arbitrarily. In general, joining by heat fusion is preferred for workability. Where heat fusion is adopted for joining, in case where the fiber material of the ultrafine hydrophobic fiber nonwoven fabric is the preferred polypropylene, it is desirable for easy heat fusion to use hydrophobic nonwoven fabric comprising polypropylene.

Preferred examples of the above-described laminates used in the kitchen sheet contemplated for multiple purposes include those of a combination of polypropylene nonwoven fabric obtained by spun bonding (hereinafter referred to PP spun-bonded) as hydrophobic nonwoven fabric and PP melt-blown as ultrafine hydrophobic fiber nonwoven fabric. More specifically, laminates of various combinations shown below are preferred, being appropriately selected and designed according to the use.

PP spun-bonded/PP melt-blown/PP spun-bonded

PP spun-bonded/PP melt-blown/PP melt-blown/PP spun-bonded

PP spun-bonded/PP melt-blown

PP melt-blown/PP spun-bonded/PP melt-blown

Particularly preferred of them is PP spun-bonded/PP melt-blown/PP spun-bonded for its broad adaptability.

The basis weight of the base sheet comprising the above-described fiber aggregate is desirably 5 to 100 g/m², more desirably 10 to 100 g/m², still more desirably 15 to 75 g/m², yet more desirably 20 to 75 g/m², particularly desirably 25 to 60 g/m², and most desirably 30 to 60 g/m². A base sheet having a basis weight less than 10 g/m² has poor shapability to unevenness and tends to be collapsed under the weight of food, which gives rise to problems such that: the passageways for letting water vapor from food escape are narrowed to cause swell of the food; drippings from frozen food on defrosting come into contact with the food; and water drops come into direct contact with a vegetable preserved as wrapped in the kitchen sheet with the unevenness collapsed. On the other hand, a base sheet having a basis weight exceeding 100 g/m² may increase the cost.

Taking flexibility for wrapping in food into consideration, the base sheet preferably has a thickness of 0.1 to 1.0 mm, particularly 0.1 to 0.5 mm.

The water pressure resistance of the base sheet is selected appropriately according to the use of the kitchen sheet of the invention. For use in steaming in, e.g., a microwave oven, a preferred water pressure resistance is 500 mmH₂O or higher. Microwave steaming is exemplified by a case in which water is put into a dish, a kitchen sheet comprising the base sheet having been shaped to prescribed unevenness is placed thereon, on which shaomai, gyoza, an-man, nikuman, cold rice, etc. is steamed.

With a higher water pressure resistance, the cooking time can be extended. Where a relatively long cooking time is needed, the water pressure resistance of the base sheet can be increased. In such a case, it is still preferred for the base sheet to have a water pressure resistance of 650 mmH₂O or higher.

5 Where the base sheet has a water pressure resistance of 500 mmH₂O or higher, the higher the air permeability of the base sheet, the more suitable as a filter of a ventilation fan or for use in steaming in a steamer or in re-heating in a microwave oven. From the standpoint of applicability to a diversity of uses, a preferred air permeability is from 5 to 100 cc/cm²/sec, particularly 5 to 50 cc/cm²/sec.

10 For use in microwave cooking such as steaming, it is demanded that the kitchen sheet wrapping the food has a steaming effect to some extent. Additionally, when food is pre-cooked in a microwave oven with being wrapped in the kitchen sheet or when a wrapped vegetable is preserved, too much water content of the food may be evaporated through the kitchen sheet. Therefore, for use in microwave cooking such as steaming, microwave pre-
15 cooking, or wrapping vegetables for preservation, it is preferred for the base sheet to have an air permeability of 5 to 10 cc/cm²/sec.

Where the base sheet has a water pressure resistance of 500 mmH₂O or higher, and, in particular, where the base sheet is a laminate containing the aforementioned ultrafine hydrophobic fiber nonwoven fabric, it is preferred for the ultrafine hydrophobic fiber
20 nonwoven fabric to have a basis weight of 1 to 50 g/m², particularly 1 to 20 g/m²; for the aforementioned thermoplastic resin nonwoven fabric to have a basis weight of 3 to 30 g/m², particularly 3 to 15 g/m²; and for the laminate as a whole to have a basis weight of 5 to 80 g/m², particularly 10 to 60 g/m².

For use in microwave cooking, for example, re-heating food, it is preferred for the
25 base sheet to have a water pressure resistance of 100 mmH₂O or more and less than 500 mmH₂O. This is preferred because, for one thing, the resulting kitchen sheet, used between food and a dish or used to wrap food, does not allow condensation to pass therethrough and may provide the food hot and dry and, for another, the resulting kitchen sheet, used in microwave pre-cooking, does not allow the water content present with food
30 to escape and achieves steaming easily. A water pressure resistance less than 100 mmH₂O

is unfavorable because food, while heated in a microwave oven, may be swollen with condensation on the turntable.

When, in particular, the kitchen sheet has a reduced height of the unevenness and is used in microwave heating, etc., it is still preferred for the base sheet to have a water pressure resistance of 200 to 500 mmH₂O to avoid swell of food.

Where the base sheet has a water pressure resistance of 100 mmH₂O or higher and lower than 500 mmH₂O, and, in particular, where the base sheet is a laminate having the above-described ultrafine hydrophobic fiber nonwoven fabric, it is preferred for the ultrafine hydrophobic fiber nonwoven fabric to have a basis weight of 1 to 20 g/m², particularly 1 to 10 g/m², especially 1 to 5 g/m²; for the thermoplastic resin nonwoven fabric to have a basis weight of 3 to 30 g/m², particularly 3 to 15 g/m²; and for the laminate as a whole to have a basis weight of 7 to 100 g/m², particularly 7 to 50 g/m², especially 7 to 20 g/m².

In the kitchen sheet of the present invention, the base sheet made of the above-described fiber aggregate is shaped to have unevenness so as to have an apparent thickness of 1.0 mm or greater, and the kitchen sheet has a compressive recovery of 30% or more.

Since the kitchen sheet has been shaped to have unevenness so as to have a compressive recovery of 30% or more, when it is used as an underlay of food to be heated in a microwave oven, it allows water vapor exuded from food to pass and, as a result, the food can be prevented from swelling with water produced by condensation of water vapor from the food. This is the case, for example, when the kitchen sheet is set on a plate, on which cooked food, such as shaomai, gyoza, an-man, nikuman, etc. is put and re-heated in a microwave oven, or when cooked preserved food, such as frozen food, is cooked. If the compressive recovery is less than 30%, the sheet undergoes change in shape when held by hand and does not restore the original shape.

The kitchen sheet with an increased height of the unevenness can be used for cooking foods emitting much water vapor. Where food needs cooking in the presence of a fairly large amount of steam, the thickness of the base sheet can be increased to fit the need. This can be achieved by making the uneven shape resistant against collapse on handling so as to keep the thickness originally given to the base sheet. It is preferred that the kitchen sheet of the present invention for such uses has a compressive recovery of 45% or more.

Since the kitchen sheet of the present invention has the base sheet shaped to have unevenness as described above, the contact area with food is diminished, and the drops of condensation on the surface of the sheet are prevented from coming into contact with food.

The shape of the unevenness is not particularly limited as long as it has concavities which connect with each other to form passageways through which water vapor generated from food can escape (concavities disposed discontinuously and regularly all over the kitchen sheet). That is, the unevenness presents passageways formed of connected concavities, playing an important role in letting water vapor generated from food escape.

When the kitchen sheet of the present invention is used to wrap in a vegetable, it reserves the water produced by condensation in the concavities of the unevenness while moderately releasing the generated water vapor. Since the water drops do not come into contact with the vegetable, the vegetable is prevented from getting rotten. Further, when food is defrosted, the kitchen sheet of the present invention can be laid under the food so that drippings can be collected in the concavities, enabling satisfactory defrosting.

When the kitchen sheet of the present invention is used as an oil filter, the unevenness serves to increase the area through which oil passes, enabling quick oil filtration.

When used as a fat and oil absorbing sheet, water vapor generated from hot deep-fried foods such as tempura and fry, is quickly released through the passageways formed of the connected concavities, and the fried food is kept away from contact with water drops collecting under the fried food. As a result, the fried food keeps crisp texture.

When the kitchen sheet of the present invention is used for dishwashing or wiping clean, the unevenness makes the sheet three-dimensional, easy to hold, and fit to complicated shapes such as dishes, a sink, and a stove, making the sheet convenient to use.

The height of the unevenness (the distance from the bottom of the uneven-shaped base sheet to the inner side of the top of the convexities) is preferably three or more times the thickness of the base sheet. With this height, concavities connecting with each other form necessary passageways for water vapor.

It is desirable that the height of the unevenness be as great as possible in order to widen the passageways for water vapor and to keep food away from condensation.

However, from the standpoint of applicability to a diversity of uses, it is more desirable that the height is 3 to 20 times the thickness of the base sheet.

The unevenness pattern preferably has a pitch (the distance between the peaks of adjacent convexities or between the valleys of adjacent concavities) of 3.5 mm or more.

5 The pitch of the unevenness pattern is selected appropriately according to the size of the food to be cooked, depending on how many convexities are to support the food. From the size of general foods, the practical upper limit of the pitch is 50 mm.

Taking various applications into consideration, the pitch of the unevenness pattern is still preferably 3.5 to 25 mm, particularly preferably 5.0 to 15 mm.

10 The apparent thickness of the kitchen sheet of the present invention (the thickness of the whole sheet inclusive of the unevenness, and more particularly the apparent thickness measured by the method described in Examples hereinafter given) is 1.0 mm or greater. If the apparent thickness is smaller than 1.0 mm, the passageways for water vapor formed of concavities connecting with each other are narrow, and the drops of condensation on the
15 kitchen sheet come into direct contact with food. While the apparent thickness of the kitchen sheet of the present invention is desirably as great as possible in order to widen the passageways for water vapor and to keep food away from condensation, the practical upper limit for actual use is 10 mm.

For applications inclusive of waterproof paper for washing, wiping, etc., the apparent
20 thickness of the kitchen sheet is preferably 1.0 to 10 mm. Various applications being taken into consideration, a still preferred apparent thickness is 1.0 to 5.0 mm.

The kitchen sheet of the present invention is produced by embossing a base sheet comprising a fiber aggregate, preferably hydrophobic fiber nonwoven fabric, having an air permeability of 5 cc/cm²/sec or more as measured according to JIS L1096A to form
25 unevenness so as to give an apparent thickness of 1.0 mm or greater and a compressive recovery of 30% or more. It is preferred to use, as the fiber aggregate, a laminate composed of a sheet of ultrafine hydrophobic fiber nonwoven fabric having on at least one side thereof nonwoven fabric made of a thermoplastic resin. It is also preferred to use a base sheet having a water pressure resistance of 100 mmH₂O or more and less than
30 500 mmH₂O or a base sheet having a water pressure resistance of 500 mmH₂O or more.

The manner of embossing is not particularly restricted. For example, a method using an embossing machine having matched steel rolls can be used. The form of the embossing machine is not particularly limited as far as the above-described unevenness pattern can be imparted.

5 Preferred conditions for embossing are as follows.

Pressure: 100 to 500 kPa, particularly 200 to 300 kPa

Temperature: 50 to 180°C, particularly 70 to 120°C

The embossed pattern made by the embossing includes polka dots, checks, zigzags, dots, and stripes.

10 As described above, since the kitchen sheet of the present invention comprises a base sheet comprising a fiber aggregate having a prescribed air permeability and having been shaped to have unevenness so as to have a prescribed apparent thickness and a prescribed compressive recovery, it is useful in the above-described diversity of applications.

Examples

15 The present invention will now be illustrated in greater detail by way of Examples, but the present invention is not construed as being limited thereto.

The methods of measurement or quantitative determination of physical properties used in Examples are shown below.

Compressive recovery:

20 A kitchen sheet is compressed by applying a load of 50 gf/cm² at a stroke speed of 50 sec/min by use of KES-TB3 supplied by KATO TECH, Inc. A compressive recovery R ($R(\%) = (Wc'/Wc) \times 100$) is obtained from the work of compression Wc (gfcm/cm²) and the work of recovery from compression Wc' (gfcm/cm²).

Water pressure resistance:

25 Measured in accordance with JIS L1092.

Air permeability:

Measured in accordance with JIS L1096A.

Apparent thickness:

An acrylic plate of 4 cm² in area is fitted to the measuring part of DIAL THICKNESS GAUGE (manufactured by PEACOCK), and the thickness of a kitchen sheet of 4 cm² in area is measured.

EXAMPLES 1 TO 3

5 The kitchen sheets of Examples 1 to 3 are shown in Table 1 below.

10 The base sheet of the kitchen sheet of Example 1 is a 3-ply laminate comprising rayon/PE air-through bonded nonwoven fabric having on both sides thereof PP spun-bonded nonwoven fabric, partially jointed into one body by heat fusion. The base sheet of the kitchen sheet of Example 2 is PP spun-bonded nonwoven fabric (a single ply). The base sheet of the kitchen sheet of Example 3 is a three-ply laminate comprising rayon/PE spun-laced nonwoven fabric having on both sides thereof PP spun-bonded nonwoven fabric, joined together by heat fusion.

 The kitchen sheets of Examples 1 to 3 were obtained as follows.

15 Each base sheet (thickness: 0.2 mm; air permeability: shown in Table 1) was embossed through hot rolls (matched steel rolls) under a pressure of 200 kPa at a temperature of 100°C to obtain a kitchen sheet having an apparent thickness of 1.7 mm and a compressive recovery shown in Table 1. The embossed pattern was polka dots arrayed in both longitudinal and lateral directions continuously and regularly. The pitch of the bosses (the distance between the peaks of adjacent convexities) was 7.0 mm.

TABLE 1

Example No.	1st Layer	2nd Layer	3rd Layer	Air Permeability (cc/cm ² /sec)	Compressive Recovery (%)
1	PP spun-bonded ^{*1} 12 g/m ²	rayon/PE air-through ^{*2} 20 g/m ²	PP spun-bonded ^{*1} 12 g/m ²	150	40
2	PP spun-bonded ^{*1} 30 g/m ²	-	-	80	42
3	PP spun-bonded ^{*1} 12 g/m ²	rayon/PE spun-laced ^{*3} 25 g/m ²	PP spun-bonded ^{*1} 12 g/m ²	120	38

*1: Hydrophobic fiber nonwoven fabric of polypropylene (average fiber diameter: 15 μ m) prepared by spun-bonding process.

*2: Nonwoven fabric made of rayon and polyethylene (weight ratio=5/5) (average fiber diameter of total fiber: 15 μ m), prepared by air-through bonding process.

*3: Nonwoven fabric made of rayon and polyethylene (weight ratio=7/3) (average fiber diameter of total fiber: 15 μ m), prepared by spun-lacing process.

In the above table, the values given below each nonwoven fabric are basis weights of the respective fabrics.

EXAMPLES 4 TO 6

The kitchen sheets of Examples 4 to 6 are shown in Table 2 below.

The base sheets used in these kitchen sheets are three-ply laminates comprising PP melt-blown nonwoven fabric having on both sides thereof PP spun-bonded nonwoven fabric, joined together by partial heat fusion.

The kitchen sheets of Examples 4 to 6 were prepared as follows. Each base sheet (thickness: 0.2 mm; water pressure resistance and air permeability: shown in Table 2 below) was made uneven by embossing through hot rolls (matched steel rolls) under a pressure of 200 kPa at a temperature of 120°C to obtain a kitchen sheet having an apparent thickness of 1.7 mm and a compressive recovery shown in Table 2. The embossed pattern was polka dots arrayed in both longitudinal and lateral directions continuously and regularly. The pitch of the bosses (the distance between the peaks of adjacent convexities) was 7.0 mm.

TABLE 2

Example No.	1st Layer	2nd Layer	3rd Layer	Water Pressure Resistance (mmH ₂ O)	Air Permeability (cc/cm ² /sec)	Compressive Recovery (%)
4	PP spun-bonded ^{*4} 12 g/m ²	PP melt-blown ^{*5} 10 g/m ²	PP spun-bonded ^{*4} 12 g/m ²	300	30	62
5	PP spun-bonded ^{*4} 5 g/m ²	PP melt-blown ^{*5} 5 g/m ²	PP spun-bonded ^{*4} 5 g/m ²	200	60	51
6	PP spun-bonded ^{*4} 5 g/m ²	PP melt-blown ^{*5} 3 g/m ²	PP spun-bonded ^{*4} 5 g/m ²	150	100	45

*4: Hydrophobic nonwoven fabric of polypropylene (average fiber diameter: 15 μ m), prepared by spun-bonding process.

*5: Ultrafine hydrophobic fiber nonwoven fabric of polypropylene (average fiber diameter: 5 μ m), prepared by melt-blowing process.

In the above table, the values given below each nonwoven fabric are basis weights of the respective fabrics.

EXAMPLES 7 TO 10

The kitchen sheets of Examples 7 to 10 are shown in Table 3 below.

The base sheets of the kitchen sheets of Examples 7, 8 and 10 are three-ply laminates comprising PP melt-blown nonwoven fabric having on both sides thereof PP spun-bonded nonwoven fabric by heat fusion. The base sheet of the kitchen sheet of Example 9 is a four-ply laminate composed of a laminate of separately prepared two PP melt-blown nonwoven webs having on both sides of the laminate PP spun-bonded nonwoven fabric, the stacked four layers simultaneously heat-fused into one body.

The kitchen sheets of Examples 7 to 10 were obtained as follows. Each base sheet (thickness: 0.2 mm; water pressure resistance and air permeability: shown in Table 3 below) was made uneven by embossing through hot rolls (matched steel rolls) under a pressure of 200 kPa at a temperature of 120°C to obtain a kitchen sheet having an apparent thickness of 1.7 mm and a compressive recovery shown in Table 3. The embossed pattern was polka dots arrayed in both longitudinal and lateral directions continuously and regularly. The pitch of the bosses (the distance between the peaks of adjacent convexities) was 7.0 mm.

TABLE 3

Example No.	1st Layer	2nd Layer	3rd Layer	4th Layer	Water Pressure Resistance (mmH ₂ O)	Air Permeability (cc/cm ² /sec)	Compressive Recovery (%)
7	PP spun-bonded* ⁶ 15 g/m ²	PP melt-blown* ⁷ 20 g/m ²	PP spun-bonded* ⁶ 15 g/m ²	-	550	33	65
8	PP spun-bonded* ⁶ 12 g/m ²	PP melt-blown* ⁷ 30 g/m ²	PP spun-bonded* ⁶ 12 g/m ²	-	680	15	70
9	PP spun-bonded* ⁶ 12 g/m ²	PP melt-blown* ⁷ 10 g/m ²	PP melt-blown* ⁷ 10 g/m ²	PP spun-bonded* ⁶ 12 g/m ²	600	30	68
10	PP spun-bonded* ⁶ 12 g/m ²	PP melt-blown* ⁷ 40 g/m ²	PP spun-bonded* ⁶ 12 g/m ²	-	1500	2	75

*6: Hydrophobic nonwoven fabric of polypropylene (average fiber diameter: 15 μ m), prepared by spun bonding process.

*7: Ultrafine hydrophobic fiber nonwoven fabric of polypropylene (average fiber diameter: 3 μ m), prepared by melt-blowing process.

PP melt-blown nonwoven fabric (40 g/m²) of Example 10 is used after it is pressed.

In the above table, the values given below each nonwoven fabric are basis weights of the respective fabrics.

Industrial Applicability:

The kitchen sheet according to the present invention is useful in various applications, for example, in cooking or defrosting food in a microwave oven, wrapping food such as vegetables for preservation in a refrigerator, wrapping meat, fish, etc. for preservation in a freezer, steaming food in a steamer, etc., draining off food, absorbing impurities or fat exuded from food in boiling, filtering oil, absorbing fat and oil, washing dishes, wiping a sink and a stove with a light scouring effect, and protecting dishes, etc. from breakage while storage, and as a draining sheet to remove water from garbage before discarding, as a filter of a ventilation fan, and so forth.

The process for producing a kitchen sheet of the present invention provides the above-described useful kitchen sheet.

CLAIMS

1. A kitchen sheet comprising a base sheet comprising a fiber aggregate having an air permeability of 5 cc/cm²/sec or more as measured in accordance with JIS L1096A, said base sheet having been shaped to have unevenness with an apparent thickness of 1.0 mm or greater, and said kitchen sheet having a compressive recovery of 30% or more.
2. A kitchen sheet according to claim 1, wherein said base sheet has a water pressure resistance of 100 mmH₂O or more and less than 500 mmH₂O as measured in accordance with JIS L1092.
3. A kitchen sheet according to claim 1, wherein said base sheet has a water pressure resistance of 500 mmH₂O or more as measured in accordance with JIS L1092.
4. A kitchen sheet according to claim 1, wherein the height of said unevenness is three or more times the thickness of said base sheet.
5. A kitchen sheet according to claim 1, wherein said unevenness is arranged at a pitch of 3.5 mm or greater.
6. A kitchen sheet according to claim 1, wherein said fiber aggregate is a laminate having two or more layers, in which the fiber material of the surface layer constituting said laminate is hydrophobic fiber.
7. A kitchen sheet according to claim 2, wherein said base sheet is a laminate having two or more layers of a fiber aggregate, in which the fiber material of the surface layer constituting said laminate is hydrophobic fiber, and the inner layer constituting said laminate is a nonwoven fabric comprising an ultrafine hydrophobic fiber.
8. A kitchen sheet according to claim 3, wherein said base sheet is a laminate having two or more layers of a fiber aggregate, in which the fiber material of the surface layer constituting said laminate is hydrophobic fiber, and the inner layer constituting said laminate is a nonwoven

fabric comprising an ultrafine hydrophobic fiber.

9. A process for producing a kitchen sheet comprising superposing a nonwoven fabric of a thermoplastic resin on at least one side of a sheet of a nonwoven fabric comprising an ultrafine hydrophobic fiber to obtain a base sheet having a water pressure resistance of 100 mmH₂O or more and less than 500 mmH₂O as measured in accordance with JIS L1092 and an air permeability of 5 cc/cm²/sec or more as measured in accordance with JIS L1096A and embossing the base sheet to impart unevenness so that the base sheet may have an apparent thickness of 1.0 mm or greater and a compressive recovery of 30% or more.

10. A process for producing a kitchen sheet comprising superposing a nonwoven fabric of a thermoplastic resin on at least one side of a sheet of a nonwoven fabric comprising an ultrafine hydrophobic fiber to obtain a base sheet having a water pressure resistance of 500 mmH₂O or more as measured in accordance with JIS L1092 and an air permeability of 5 cc/cm²/sec or more as measured in accordance with JIS L1096A and embossing the base sheet to impart unevenness so that the base sheet may have an apparent thickness of 1.0 mm or greater and a compressive recovery of 30% or more.

ABSTRACT

The kitchen sheet of the present invention comprises a base sheet comprising a fiber aggregate having an air permeability of 5 cc/cm²/sec or more as measured in accordance with JIS L1096A, the base sheet having been shaped to have unevenness with an apparent thickness of 1.0 mm or greater, and has a compressive recovery of 30% or more.

Declaration and Power of Attorney For Patent Application

特許出願宣言書及び委任状

Japanese Language Declaration

日本語宣言書

下記の氏名の発明者として、私は以下の通り宣言します。

As a below named inventor, I hereby declare that:

私の住所、私書箱、国籍は下記の私の氏名の後に記載された通りです。

My residence, post office address and citizenship are as stated next to my name.

下記の名称の発明に関して請求範囲に記載され、特許出願している発明内容について、私が最初かつ唯一の発明者（下記の氏名が一つの場合）もしくは最初かつ共同発明者（下記の名称が複数の場合）であると信じています。

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled.

"KITCHEN SHEET"

上記発明の明細書は、

the specification of which

☐ 本書に添付されています。

☐ is attached hereto.

☐ ____月____日に提出され、米国出願番号または特許協定条約国際出願番号を____とし、
(該当する場合) ____に訂正されました。

☒ was filed on November 17, 1998
as United States Application Number or
PCT International Application Number
PCT/JP98/05167 and was amended on
____ (if applicable).

私は、特許請求範囲を含む上記訂正後の明細書を検討し、内容を理解していることをここに表明します。

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

私は、連邦規則法典第37編第1条56項に定義されるとおり、特許資格の有無について重要な情報を開示する義務があることを認めます。

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56.

Japanese Language Declaration
(日本語宣言書)

私は、米国法典第35編119条 (a) - (d) 項又は365条 (b) 項に基づき下記の、米国以外の国の少なくとも一カ国を指定している特許協力条約365 (a) 項に基づく国際出願、又は外国での特許出願もしくは発明者証の出願についての外国優先権をここに主張するとともに、優先権を主張している、本出願の前に出願された特許または発明者証の外国出願を以下に、枠内をマークすることで、示しています。

Prior Foreign Application(s)

外国での先行出願

9-329067

Japan

(Number)

(Country)

(番号)

(国名)

9-329068

Japan

(Number)

(Country)

(番号)

(国名)

9-329069

Japan

私は、第35編米国法典119条 (e) 項に基づいて下記の米国特許出願規定に記載された権利をここに主張いたします。

(Application No.)
(出願番号)

(Filing Date)
(出願日)

私は、下記の米国法典第35編120条に基づいて下記の米国特許出願に記載された権利、又は米国を指定している特許協力条約365条 (c) に基づく権利をここに主張します。また、本出願の各請求範囲の内容が米国法典第35編112条第1項又は特許協力条約で規定された方法で先行する米国特許出願に開示されていない限り、その先行米国出願書提出日以降で本出願書の日本国内または特許協力条約国際提出日までの期間中に入手された、連邦規則法典第37編1条56項で定義された特許資格の有無に関する重要な情報について開示義務があることを認識しています。

(Application No.)
(出願番号)

(Filing Date)
(出願日)

(Application No.)
(出願番号)

(Filing Date)
(出願日)

私は、私自信の知識に基づいて本宣言書中で私が行なう表明が真実であり、かつ私の入手した情報と私の信じているところに基づく表明が全て真実であると信じていること、さらに故意になされた虚偽の表明及びそれと同等の行為は米国法典第18編第1001条に基づき、罰金または拘禁、もしくはその両方により処罰されること、そしてそのような故意による虚偽の声明を行なえば、出願した、又は既に許可された特許の有効性が失われることを認識し、よってここに上記のごとく宣誓を致します。

I hereby claim foreign priority under Title 35, United States Code, Section 119 (a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or Section 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed.

Priority Claimed

優先権主張

28/November/1997

☒

☐

(Day/Month/Year Filed)
(出願年月日)

Yes
はい

No
いいえ

28/November/1997

☒

☐

(Day/Month/Year Filed)
(出願年月日)

Yes
はい

No
いいえ

28/November/1997

☒ Yes

I hereby claim the benefit under Title 35, United States Code, Section 119(e) of any United States provisional application(s) listed below.

(Application No.)
(出願番号)

(Filing Date)
(出願日)

I hereby claim the benefit under Title 35, United States Code, Section 120 of any United States application(s), or Section 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code Section 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of application.

(Status: Patented, Pending, Abandoned)
(現況: 特許許可済、係属中、放棄済)

(Status: Patented, Pending, Abandoned)
(現況: 特許許可済、係属中、放棄済)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Japanese Language Declaration
(日本語宣言書)

委任状：私は下記の発明者として、本出願に関する一切の手続きを米特許商標局に対して遂行する弁理士または代理人として、下記の者を指名いたします。
(弁理士、または代理人の指名及び登録番号を明記のこと)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith: (list name and registration number)

Norman F. Oblon, Reg. No. 24,618; Marvin J. Spivak, Reg. No. 24,913; C. Irvin McClelland, Reg. No. 21,124; Gregory J. Maier, Reg. No. 25,599; Arthur I. Neustadt, Reg. No. 24,854; Richard D. Kelly, Reg. No. 27,757; James D. Hamilton, Reg. No. 28,421; Eckhard H. Kuesters, Reg. No. 28,870; Robert T. Pous, Reg. No. 29,099; Charles L. Gholz, Reg. No. 26,395; William E. Beaumont, Reg. No. 30,996; Robert F. Gnuse, Reg. No. 27,295; Jean-Paul Lavalleye, Reg. No. 31,451; Stephen G. Baxter, Reg. No. 32,884; Robert W. Hahl, Reg. No. 33,893; Richard L. Treanor, Reg. No. 36,379; Steven P. Weihrouch, Reg. No. 32,829; John T. Goolkasian, Reg. No. 26,142; Richard L. Chinn, Reg. No. 34,305; Steven E. Lipman, Reg. No. 30,011; Carl E. Schlier, Reg. No. 34,426; James J. Kulbaski, Reg. No. 34,648; Richard A. Neifeld, Reg. No. 35,299; J. Derek Mason, Reg. No. 35,270; Surinder Sachar, Reg. No. 34,423; Christina M. Gadiano, Reg. No. 37,628; Jeffrey B. McIntyre, Reg. No. 36,867; Paul E. Rauch, Reg. No. 38,591; William T. Enos, Reg. No. 33,128 and Michael E. McCabe, Jr., Reg. No. 37,182, with full powers of substitution and revocation.

書類送付先

Send Correspondence to:

OBLON, SPIVAK, McCLELLAND, MAIER & NEUSTADT, P.C.
FOURTH FLOOR
1755 JEFFERSON DAVIS HIGHWAY
ARLINGTON, VIRGINIA 22202 U.S.A.

直接電話連絡先：(名前及び電話番号)

Direct Telephone Calls to: (name and telephone number)

(703) 413-3000

単独発明者または第一の共同発明者の氏名	Full name of sole or first joint inventor
<u>Nobuya SATO</u>	<u>Nobuya SATO</u>
発明者の署名	Inventor's signature
<u>Nobuya Sato</u>	<u>Nobuya Sato</u>
住所	Residence
<u>TOCHIGI, JAPAN</u>	<u>TOCHIGI, JAPAN</u>
国籍	Citizenship
	Japanese
郵便の宛先	Post Office Address
	c/o Kao Corporation, Research Laboratories, 2606, Akabane, Ichikai-machi, Haga-gun, TOCHIGI 321-3426 JAPAN
第二の共同発明者の氏名	Full name of second joint inventor, if any
<u>Haruo SAKAHASHI</u>	<u>Haruo SAKAHASHI</u>
第二の共同発明者の署名	Second joint Inventor's signature
<u>Haruo Sakahashi</u>	<u>Haruo Sakahashi</u>
住所	Residence
<u>TOCHIGI, JAPAN</u>	<u>TOCHIGI, JAPAN</u>
国籍	Citizenship
	Japanese
郵便の宛先	Post Office Address
	c/o Kao Corporation, Research Laboratories, 2606, Akabane, Ichikai-machi, Haga-gun, TOCHIGI 321-3426 JAPAN

(第三以降の共同発明者についても同様に記載し、署名すること)

(Supply similar information and signature for third and subsequent joint inventors.)

Japanese Language Declaration
(日本語宣言書)

第三の共同発明者の氏名	Full name of third joint inventor, if any Masahito MATSUDA
第三の共同発明者の署名 日付	Third joint Inventor's signature Date Masahito Matsuda April 14, 2000
住所	Residence TOCHIGI, JAPAN JAX
国籍	Citizenship Japanese
郵便の宛先	Post Office Address c/o Kao Corporation, Research Laboratories, 2606, Akabane, Ichikai-machi, Haga-gun, TOCHIGI 321-3426 JAPAN

第四の共同発明者の氏名	Full name of fourth joint inventor, if any
第四の共同発明者の署名 日付	Fourth joint Inventor's signature Date
住所	Residence
国籍	Citizenship
郵便の宛先	Post Office Address

第五の共同発明者の氏名	Full name of fifth joint inventor, if any
第五の共同発明者の署名 日付	Fifth joint Inventor's signature Date
住所	Residence
国籍	Citizenship
郵便の宛先	Post Office Address

第六の共同発明者の氏名	Full name of sixth joint inventor, if any
第六の共同発明者の署名 日付	Sixth joint Inventor's signature Date
住所	Residence
国籍	Citizenship
郵便の宛先	Post Office Address

(第六またはそれ以降の共同発明者に対しても同様な情報および署名を提供すること。)

(Supply similar information and signature for third and subsequent joint inventors.)